
IN THE CLAIMS

- 1. (Original) A radiation-sensitive resin composition comprising:
- (A) a resin comprising at lest two recurring units of the following formulas (1) (6),



wherein R¹ represents a hydrogen atom or methyl group and R² represents a substituted or unsubstituted alkyl group having 1-4 carbon atoms, two or more R² groups that may be present being either the same or different, in the total amount of 5 - 7 mol %, but each in the amount of 1 - 49 mol %, the resin being insoluble or scarcely soluble in alkali, but becoming easily soluble in alkali by the action of an acid, and

(B) a photoacid generator.

2. (Original) The radiation-sensitive resin composition according to Claim 1, wherein the photoacid generator (B) is compound shown by the formula (7),

$$\begin{array}{c|c}
R^3 \\
(R^4)_m \\
(7) \\
R^5 \\
R^5
\end{array}$$

wherein R³ represents a hydrogen atom, hydroxyl group, linear or branched alkyl group having 1 - 10 carbon atoms, linear or branched alkoxyl group having 1 - 10 carbon atoms, or linear or branched alkoxycarbonyl group having 2 - 11 carbon atoms, R⁴ represents a linear or branched alkyl group having 1 -10 carbon atoms, R⁵ individually represents a linear or branched alkyl group having 1 - 10 carbon atoms, substituted or unsubstituted phenyl group, or substituted or unsubstituted naphthyl group, or two R⁵ groups bond to form a substituted or unsubstituted divalent group having 2 - 10 carbon atoms, k is an integer of 0 to 2, X⁻ represents an anion represented by the formula R⁶C_nF_{2n}SO₃⁻ (wherein R⁶ represents a fluorine atom or substituted or unsubstituted monovalent hydrocarbon group and n is an integer of 1 to 10), and m is an integer of 1 to 10.

3. (Original) The radiation-sensitive resin composition according to Claim 1, wherein the resin (A) and the photoacid generator (B) are dissolved in a solvent comprising at least one compound selected from the group consisting of propylene glycol mono-methyl ether acetate, 2-heptanone, and cyclohexanone.

4. (Previously Presented) A radiation-sensitive resin composition comprising: a resin comprising at least two recurring units of the following formulas (1) - (3),

wherein R¹ represents a hydrogen atom or methyl group and R² represents a substituted or unsubstituted alkyl group having 1 - 4 carbon atoms, two or more R² groups that may be present being either the same or different, in the total amount of 5 - 70 mol %, but each in the amount of 1 - 49 mol %, the resin being insoluble or scarcely soluble in alkali, but becoming easily soluble in alkali by the action of an acid, and

- (B) a photoacid generator.
- 5. (Previously Presented) The radiation-sensitive resin composition according to Claim 4, wherein the photoacid generator (B) is the compound shown by the formula (7),

$$\begin{array}{c|c}
R^3 \\
(R^4)_m \\
(7) \\
R^5 \\
R^5
\end{array}$$

wherein R³ represents a hydrogen atom, hydroxyl group, linear or branched alkyl group having 1 - 10 carbon atoms, linear or branched alkoxyl group having 1 - 10 carbon atoms, or linear or branched alkoxycarbonyl group having 2 -11 carbon atoms, R⁴ represents a linear or branched alkyl group having 1 - 10 carbon atoms, R⁵ individually represents a linear or branched alkyl group having 1 - 10 carbon atoms, substituted or unsubstituted phenyl group, or substituted or unsubstituted naphthyl group, or two R⁵ groups bond to form a substituted or unsubstituted divalent group having 2 - 10 carbon atoms, k is an integer of 0 to 2, X⁻ represents an anion represented by the formula R⁶C_nF_{2n}SO₃⁻ (wherein R⁶ represents a fluorine atom or substituted or unsubstituted monovalent hydrocarbon group and n is an integer of 1 to 10), and m is an integer of 1 to 10.

- 6. (Previously Presented) The radiation-sensitive composition according to Claim 4, wherein the resin (A) and the photoacid generator (B) are dissolved in a solvent comprising at least one compound selected from the group consisting of propylene glycol mono-methyl ether acetate, 2-heptanone, and cyclohexanone.
 - 7. (Previously Presented) A radiation-sensitive resin composition comprising,(A) a resin comprising at least one recurring unit of the following formulas (1) (3),

wherein R¹ represents a hydrogen atom or methyl group and R² is a methyl group, and at least one recurring unit of the above formulas (1) - (3), wherein R¹ represents a hydrogen atom or methyl group and R² represents a substituted or unsubstituted alkyl group having 1 - 4 carbon atoms, excluding a methyl group, two or more R² groups that may be present being either the same or different, in the total amount of 5 - 70 mol %, but each in the amount of 1 - 49 mol %, the resin being insoluble or scarcely soluble in alkali, but becoming easily soluble in alkali by the action of an acid, and

- (B) a photoacid generator.
- 8. (Previously Presented) The radiation-sensitive resin composition according to Claim 7, wherein the photoacid generator (B) is the compound shown by the formula (7),

$$\begin{array}{c|c}
R^{3} \\
(R^{4})_{m} \\
(7) \\
R^{5} \\
R^{5}
\end{array}$$

wherein R³ represents a hydrogen atom, hydroxyl group, linear or branched alkyl group having 1 - 10 carbon atoms, linear or branched alkoxyl group having 1 - 10 carbon atoms, or linear or branched alkoxycarbonyl group having 2 - 11 carbon atoms, R⁴ represents a linear or branched alkyl group having 1 - 10 carbon atoms, R⁵ individually represents a linear or branched alkyl group having 1 -10 carbon atoms, substituted or unsubstituted phenyl group, or substituted or unsubstituted naphthyl group, or two R⁵ groups bond to form a substituted or unsubstituted divalent group having 2 - 10 carbon atoms, k is an integer of 0 to 2, X⁻ represents an anion represented by the formula R⁶C_nF_{2n}SO₃⁻ (wherein R⁶ represents a fluorine atom or substituted or unsubstituted monovalent hydrocarbon group and n is an integer of 1 to 10), and m is an integer of 1 to 10.

- 9. (Previously Presented) The radiation-sensitive resin composition according to Claim 7, wherein the resin (A) and the photoacid generator (B) are dissolved in a solvent comprising at least one compound selected from the group consisting of propylene glycol mono-methyl ether acetate, 2-heptanone, and cyclohexanone.
 - 10. (Previously Presented) A radiation-sensitive resin composition comprising,
 - (A) a resin comprising at least one recurring unit of the following formula (6),

$$\begin{array}{c}
R^{1} \\
CH_{2} \\
C = 0
\end{array}$$

$$\begin{array}{c}
R^{2} \\
R^{2} \\
\end{array}$$

$$\begin{array}{c}
(6)
\end{array}$$

wherein R^2 is a methyl group, and at least one recurring unit selected from the group consisting of the recurring units of the formulas (1) - (3),

wherein R¹ represents a hydrogen atom or methyl group and R² is a methyl group, in the total amount of 5 - 70 mol %, but each in the amount of 1 - 49 mol %, the resin being insoluble or scarcely soluble in alkali, but becoming easily soluble in alkali by the action of an acid, and

(B) a photoacid generator.

11. (Previously Presented) The radiation-sensitive resin composition according to Claim 10, wherein the photoacid generator (B) is the compound shown by the formula (7),

$$\begin{array}{c|c}
R^3 \\
(R^4)_m \\
(7) \\
R^5 \\
R^5
\end{array}$$

wherein R^3 represents a hydrogen atom, hydroxyl group, linear or branched alkyl group having 1-10 carbon atoms, linear or branched alkoxyl group having 1-10 carbon atoms, or linear or branched alkoxycarbonyl group having 2-11 carbon atoms, R^4 represents a linear or branched alkyl group having 1-10 carbon atoms, R^5 individually represents a linear or branched alkyl group having 1-10 carbon atoms, substituted or unsubstituted phenyl group, or substituted or unsubstituted naphthyl group, or two R^5 groups bond to form a substituted or unsubstituted divalent group having 2-10 carbon atoms, k is an integer of 0 to 2, X^- represents an anion represented by the formula $R^6C_nF_{2n}SO_3^-$ (wherein R^6 represents a fluroine atom or substituted or unsubstituted monovalent hydrocarbon group and n is an integer of 1 to 10), and m is an integer of 1 to 10.

12. (Previously Presented) The radiation-sensitive resin composition according to Claim 10, wherein the resin (A) and the photoacid generator (B) are dissolved in a solvent comprising at least one compound selected from the group consisting of propylene glycol monomethyl ether acetate, 2-heptanone, and cyclohexanone.